

WearAll Alkyd Enamel Semi Gloss - F235 Series

Product Description

Wearall Alkyd Semi-Gloss White is a white rust inhibitive semi gloss finish designed to withstand multiple washings and maring. It has great leveling characteristics and will adhere to most primed surfaces.

Recommended Use

Any vertical or horizontal surface (not be walked on) that is in need of a durable, abrasion resistant white topcoat.

General Surface Preparation

Surfaces to be painted must be free of dust, dirt, grease, loose paint, oil, glue size, calcimine, wax, soap and other surface contamination.

Ferrous Metal - Clean, then prime with FixAll Rust Inhibiting Metal Primer.

Previously Painted Surfaces - Wash, sand or dust and remove any loose paint to obtain a paintable surface.

Glossy Surfaces - Dull by sanding to insure proper adhesion of paint..

Application

Apply as thinly as possible using a multi-coat system on new surfaces.

Clean up

Clean tools and equipment with mineral spirits or turpentine. Do not use water on natural bristle or china bristle brushes.

Architectural Specifications

Ferrous Metal - Un-primed:

1 coat Rust Inhibiting Metal Primer

1 or 2 coats Wearall Alkyd Semi-Gloss White F23500

Precautions

Do not apply when air or surface temperature is below 50° F or when moisture is evident. Do not mix with latex paint. Inadequate ventilation will retard drying time. Two thin coats provides a better finish than one thick coat.

Environmental Health and Safety Information

WearAll Alkyd Enamel Semi Gloss - F235 Series

*Depending upon color choice, non zero VOC colorant added to this product may significantly increase VOC levels.

WARNING: This product contains a chemical known to the State of California to cause cancer, birth defects or other reproductive harm.

Lead Warning ! - If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

All equipment must be grounded and non-sparking tools and appropriate footwear should be used.

Always use any paint product with proper ventilation. Provide general dilution or local exhaust ventilation in volume and pattern to keep the air contaminant concentration below the applicable exposure limit (OSHA PEL) of the components being used. This information is listed on the appropriate Material Safety Data Sheets. All application areas should be ventilated in accordance with applicable OSHA regulations, contact your local office for specific information.

In an enclosed area and as required, always wear an appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application of any coating unless air monitoring demonstrates that vapor/mist levels are below applicable limits. Follow respirator manufacturer's directions for respirator use.

CAUTION! Combustible Liquid: Keep away from heat and flame. Close container after each use. Use only with adequate ventilation. Wash thoroughly after handling. In case of spillage, absorb with inert material and dispose of in accordance with applicable regulations. KEEP OUT OF REACH OF CHILDREN.

USE COMPLETELY OR DISPOSE OF PROPERLY: Dispose of in accordance with applicable Federal, State and Local regulations. Under the Resource Conservation and Recovery Act (RCRA) regulations, it is the responsibility of the product user to determine, at the time of disposal, whether a material should be classified as a hazardous waste. For recycling guidance of any unused amount, contact your local or provincial organization of recovery, recycling and disposal for regulations.

Place the rags in an empty metal container that has a tight metal lid such as a paint or stain can. Fill the container with water until the rags are submerged; Fill Place the metal lid tightly over the water soaked formerly combustible rags. Place lid tightly on container. Coontact local municipal offices for disposal directions. Never dump solvent down any household or external drains or in any open water.

Technical Data	
Product Type	Industrial
Exposure	Interior
Specular Gloss	57° ± 5
Volume Solids	51.2% ± 2
Weight Solids	69.0% ± 2
Vehicle Solids	64.3% ± 2
Pigment	35.7% ± 2
Wet Film Thickness	4 mils
Dry Film Thickness	2 mils
Viscosity @ 77 °F	87KU ± 5
Max VOC	380 g/l
Flash Point ° F	103°F
Thinner	Mineral Spirits
Clean - up	Mineral Spirits
Surface Spread Rate	
Smooth	400-450 s.f./gal.
Porous	250-350 s.f./gal.
<i>(Spray Application is 50% of above)</i>	
Drying Times	
To Touch	4 hours
To Handle	16 hours
To Recoat	12 hours
To Wash	3 days
<i>(@ 70 - 77 °F, 50% R.H)</i>	
Surface Temperature At Application	
Maximum: Over 50°F	Maximum: Under 90°F
Storage Temperature	
Store Between Over 40°F to Under 100°F	
Tools & Equipments	
Brush	Natural Bristle
Roller	Short Nap Synthetic or Natural
Airless Spray	.011 to .013 Tip
Available Package Sizes	
Gallon	
<i>(Weight Per Gallon:10.1 lbs. ± .5 lb)</i>	
Available Colors and Bases	
Available in 0 stock colors	

Notes

WearAll Alkyd Enamel Semi Gloss - F235 Series